

TECHNICAL DATA SHEET

F

Doc. Nr. TDS_4-500 Version: 2016_01

2K HS SURFACER 4–500

A two-component high solid acrylic primer filler for car and truck repair. Eurolux 2K HS Surfacer 4-500 has high anti-corrosion, hiding, mechanical and adhesion properties. In our production the Surfacer is dispersed over the pearlmill. For this reason the Eurolux 2K HS Surfacer has a very fine grinding structure, which ensures a smooth surface. Fast drying and easy sanding properties. Also possible to spray wet-in-wet.

Available in colours: Grey – Dark-grey – Black – White

Only for professional use.

0:0:0	Mixing ratio (by volume), at 20ºC	100% 2K HS Surfacer 4-500 25% 2K Hardener 2-50 0 – 15% 2K Thinner 3-50 Std / 3-51 Fast
	Potlife	ca. 2 – 3 hr
∏ s	Sprayviscosity, DIN 4, at 20°C	20 - 30 s
	Application method	1,6 – 1,8 mm 3,5 – 4,5 bar
	Number of spraycoats	1 – 3; Film thickness 60 – 120 μm
	Flash off at 20ºC	10 - 15 min
	Drying time at 20℃: 60℃:	2 – 3 hr 30 min
Theretical coverage		8 - 9 m²/l (60 μm dry film thickness)
VOC-regulation		VOC-compliant 2004/42/IIB(c)(540)<540
Storage		Keep away from sources of ignition. Store separately from flammable substances. Keep container tightly closed in a dry and well ventilated place. Storage temperature above 3 ℃.
Shelf-life		2 years
The in this leaflet supplied details and advises are based on our experiences and best knowledge. The user will be deemed to have satisfied himself independently of the suitability of the product for his own particular purpose. Guarantees cannot be claimed from this leaflet.		