

TECHNICAL DATA SHEET



Doc. Nr. TDS_7-500

Version: 2022_01







1K BASECOAT
7-500

A one-component quick drying coating with metallic, pearl and xirallic effect.

Eurolux 1K Basecoat 7-500 is a fast drying coating with excellent adhesion and good flow characteristics.

Available in silver, pearl and xirallic colours.

Use according to Directive 2004/42/EC - coatings designed for application as topcoats requiring special properties - subcategory (e).

	Mixing ratio (by volume), at 20°C	100% 1K Basecoat 7-500 80 - 100% 1K Basecoat Thinner 3-80 Std / 3-81 Fast / 3-82 Slow
	Potlife	-
	Sprayviscosity, DIN 4, at 20°C	16 – 19 s
	Application method	1,3 – 1,4 mm 2,0 – 2,5 bar
	Number of spraycoats	2 ; Film thickness 30 – 50 µm For metallic, pearl and xirallic effects follow with a lighter matching coat.
	Flash off at 20°C	2 - 5 min
	Drying time at 20°C:	5 -10 min
	Theretical coverage	10m²/l (30 µm dry film thickness)
	Storage	Keep away from sources of ignition. Store separately from flammable substances. Keep container tightly closed in a dry and well ventilated place. Storage temperature above 3°C.
	Shelf-life	3 years

The in this leaflet supplied details and advises are based on our experiences and best knowledge. The user will be deemed to have satisfied himself independently of the suitability of the product for his own particular purpose. Guarantees cannot be claimed from this leaflet.