

## TECHNICAL DATA SHEET









Doc. Nr. TDS\_6-020

Version: 2018\_01

### GLASSFIBRE PUTTY 6-020

**Eurolux 6-020 Glassfibre Putty is a polyester putty, reinforced with special-cut fiberglass. Recommended for filling and reinforcing the surfaces affected by corrosion. The large quantity of long fibres gives the product a high mechanical resistance and good filling power for repairing irregularities and holes. The Putty is characterized by very high adhesion to steel, galvanized steel, aluminium, polyester laminates and old paint layers. Furthermore the Putty has high mechanical strength. Easy to apply and process. Smooth sanding. Only for professional use.**

|   |  |  |
|---|--|--|
|    | <b>Surface preparation</b>               | Degrease, abrade and clear the surface.  |
|    | <b>Surface preparation</b>               | Degrease again and dry thoroughly.   |
|  | <b>Mixing ratio (by weight), at 20°C</b> | 100% Glassfibre Putty 6-020<br>2 - 3% Curing agent<br>Mix thoroughly 100 parts by weight of the putty with 2-3 parts by weight of the curing agent until a uniform colour is obtained.<br>Using too much hardener can result in discolouration of the topcoat. |
|  | <b>Application</b>                       | Apply the putty in thin layers within 4 -5 minutes / 20°C from mixing the curing agent. Applying temperature should be at least 10°C.  |
|  | <b>Drying time at 20°C:</b>              | 20 – 30 min.   |
|  | <b>Sanding</b>                           | Course sanding should be done with sandpaper P80 – P120.<br>Finishing sanding should be done with sandpaper P120 – P240.   |
|   | <b>VOC-regulation</b>                    | VOC-compliant.<br>Max VOC content in ready to use product 250 g/lit.   |
|   | <b>Storage</b>                           | Keep away from sources of ignition. Store separately from flammable substances. Keep container tightly closed in a dry and well ventilated place. Storage temperature above 3°C.   |
|   | <b>Shelf-life</b>                        | 2 years  |

The in this leaflet supplied details and advises are based on our experiences and best knowledge. The user will be deemed to have satisfied himself independently of the suitability of the product for his own particular purpose. Guarantees cannot be claimed from this leaflet.