







TECHNICAL DATA SHEET



Doc. Nr. TDS_1-110

Version: 2022-01

2K CLEARCOAT 1-110

<p>Eurolux 2K Clearcoat 1-110 is a quick drying, easy to apply, non-yellowing clearcoat with excellent chemical and mechanical properties. Strong UV-protection. Suitable for car and truck repair as a finish topcoat. Air drying and forced drying. Provides a long-term surface protection and has excellent adhesion on solvent borne and waterborne basecoats. Only for professional use.</p>		
	Mixing ratio (by volume), at 20°C	<p>100% 2K Clearcoat 1-110</p> <p>50% 2K Universal Hardener 2-110 Std / 2-111 Fast</p> <p>0 – 5% 2K Thinner 3-50 Std / 3-51 Fast / 3-52 Slow</p>
	Potlife	ca. 2 – 3 hr
	Sprayviscosity, DIN 4, at 20°C	17 – 20 s
	Application method	<p>1,3 – 1,5 mm</p> <p>2,5 – 3,5 bar</p>
	Number of spraycoats	2; Film thickness 40 – 60 µm
	Flash off at 20°C	5 - 10 min
	Drying time at 20°C: 60°C:	<p>6 – 8 hr</p> <p>20 – 35 min</p>
	Theoretical coverage	8-9 m ² /l (50 µm dry film thickness)
	VOC-regulation	<p>VOC-compliant</p> <p>2004/42/IB(e)(840)580</p>
	Storage	<p>Keep away from sources of ignition. Store separately from flammable substances. Keep container tightly closed in a dry and well ventilated place.</p> <p>Storage temperature above 3°C.</p>
	Shelf-life	4 years
<p>The in this leaflet supplied details and advises are based on our experiences and best knowledge. The user will be deemed to have satisfied himself independently of the suitability of the product for his own particular purpose. Guarantees cannot be claimed from this leaflet.</p>		