

## TECHNICAL DATA SHEET









Doc. Nr. TDS\_1-920

Version: 2022-01

### 2K HS EXPRESS CLEARCOAT 1-920

**Eurolux 2K HS Express Clearcoat 1-920 is a HS Clearcoat with short drying-times.**

**Very high durability, non-yellowing and excellent chemical and mechanical properties. High solid content. Strong UV-protection. Easy application. Suitable for car and truck repair. Air drying and forced drying. Provides a long-term surface protection and has excellent adhesion on solvent borne and waterborne basecoats. Only for professional use.**

	<b>Mixing ratio (by volume), at 20°C</b>	<b>100% 2K HS Clearcoat 1-920 50% 2K HS Hardener 2-200</b>
	<b>Potlife</b>	<b>1 hr</b>
	<b>Sprayviscosity, DIN 4, at 20°C</b>	<b>17 – 20 s</b>
	<b>Application method</b>	<b>1,3 – 1,4 mm 2,0 – 2,5 bar</b>
	<b>Number of spraycoats</b>	<b>1 - 2 ; Film thickness 40 – 60 µm</b>
	<b>Flash off at 20°C</b>	<b>3 min</b>
	<b>Drying time at 20°C: 60°C:</b>	<b>2 hr 15 min</b>
	<b>Theoretical Coverage</b>	<b>10 - 12 m²/l (50 µm dry film thickness)</b>
	<b>VOC-regulation</b>	<b>VOC-compliant 2004/42/IIIB(e)(840)590</b>
	<b>Storage</b>	<b>Keep away from sources of ignition. Store separately from flammable substances. Keep container tightly closed in a dry and well ventilated place. Storage temperature above 3°C.</b>
	<b>Shelf-life</b>	<b>4 years</b>

The in this leaflet supplied details and advises are based on our experiences and best knowledge. The user will be deemed to have satisfied himself independently of the suitability of the product for his own particular purpose. Guarantees cannot be claimed from this leaflet.